



3D Tiles are manufactured by Autex Industries Ltd and Autex Australia Pty Ltd under an ISO 9001 and ISO 14001 certified Quality Environmental Management Systems. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

**Specification**

**Product name** 3D Tiles  
**Description** 100% polyester thermally molded, needle punched tile

		Imperial
Tile dimensions	Classic	22.6" x 22.6"
	S5.46	19.6" x 22.6"
	S5-50	11.3" x 22.5"
Tile tolerance		(+/- 0.02") (+/- 0.02")
Thickness		Tiles range from 1" to 5 1/2" Refer to Data Sheet for specific thickness values.
Depth tolerance		(+/- 0.02")
Weight		1680 gsm

**Physical description/  
properties**

Boiling point:	N/A
Melting point:	482°F
Vapor pressure:	N/A
Specific gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative vapor density:	N/A

**Acoustic performance**

3D Tiles are specifically designed to reduce and control reverberated noise and echo in building interiors.

Minimum Noise Reduction Coefficient (NRC): 0.75

Frequency (Hz)	125	250	500	1000	2000	4000	NRC
● 3D Tiles	0.15	0.45	0.65	0.90	0.90	0.80	0.75
● 3D Tiles S-5.37, S-5.46	0.15	0.65	0.60	0.70	0.75	0.70	0.65



---

## Service

For further information about 3D Tiles or any other Autex Acoustics product, please contact your account manager or visit our website.

---

## Care and maintenance

Maintain in accordance with the Care and Maintenance Guide available for this product.

---

## Product specifications

### Composition

100% polyester fiber from polyethylene terephthalate (PET). 3D Tiles contains a minimum of 55% recycled polyester fibre.

### Suitable applications

Decorative and functional acoustic tile for retail, education, hospitality and commercial interiors.

### Fire ratings

3D Tiles have been evaluated using the following test methods:

#### ISO 9705: 1993

Classification: Group 1-S  
Smoke production rate:  
<5.0m<sup>2</sup>/s  
As required by NZBC C/VM2

#### AS ISO 9705 - 2003

Classification: Group 1  
(SMOGR<sub>Arc</sub>): <100m<sup>2</sup>/s<sup>2</sup>  
Assessed using methodology AS ISO 9705:2003 in accordance with AS 5637.1:2015 as required by BCA Specification C1.10-4

FAR 4055

### EN13501-1:2007+A1:2009

(6 mm 3D Tiles)

B - s1, d2  
Report W/F 336913

### ASTM E84 - 14

(12 mm 3D Tiles)

Class A, FS:0 - SD:10  
Report RJ3297-10

### VOC emissions

Autex Acoustics polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered a low VOC product. VOC concentration: 0.009 mg/m<sup>3</sup> (7 days).

### Water vapor sorption

ASTM C1104 / C1104M-13a  
Test conditions: 49°C, 95%RH  
Water vapor absorbed and adsorped after 4 days:  
0.4% by weight.

### Microbial resistance

ASTM G21-15  
Growth rating: 0 (No growth)  
3D Tiles do not promote the growth of molds and mildew.

### Color fastness to light

3D Tiles are suitable for indoor use only. Light fastness is dependent on use and exposure. 3D Tiles has been evaluated to the following standard: ISO 105-B02:2014  
Rating: 6 (Highest = 7)

### Color fastness to rubbing

ISO 105-X12:2016  
Dry rating: 4-5 (Highest = 5)  
Wet rating: 4-5 (Highest = 5)

### Pattern repeat

Non-woven. No pattern repeat, but the product has a directional grain. Product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

### Fabric care

Blot spills from fabric quickly. Wipe with a damp cloth. Avoid rubbing and using excessive amounts of water as this will affect the finish. Use carpet or upholstery shampoo as directed.

Blot with a clean, dry cloth after each application of the solution.

Custom printed 3D Tiles require the service of a specialist cleaning company. Refer to the 3D Tiles Care and Maintenance Guide for more information.

---

#### ● Autex Industries Ltd

702-718 Rosebank Rd  
Private Bag 19988  
Avondale 1746, Auckland  
New Zealand  
Freephone 0800 428 839  
Phone +64 9 828 9179  
Fax +64 9 828 5810

#### ● Autex Australia Pty Ltd

166 Bamfield Road  
PO Box 5099  
West Heidelberg, Melbourne  
VIC 3081, Australia  
Freephone 1800 678 160  
Phone +61 3 9457 6700  
Fax +61 3 9457 1020

#### ● Autex Acoustics Ltd

Unit J4, Lowfields Way,  
Lowfields Business Park,  
Elland, West Yorkshire  
Hx5 9Da  
United Kingdom  
Phone +44 0 1422418899

#### ● Autex Acoustics LLC

1630 Dan Kipper Dr,  
Riverside, CA 92507  
United States of America  
Phone +1 424 203 1813

An ISO 9001, ISO 14001 and ISO 45001 certified company. The brand names and logos mentioned herein are registered or unregistered trademarks either owned or used under license by Autex Industries Limited or other members of the Autex Group. The contents of this document are protected by Copyright 2021 Autex Industries Ltd. All Rights Reserved. It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.